

ARMY RESEARCH LABORATORY



Poisson's Ratio for Poled Electroceramics

Arthur Ballato

ARL-TR-432

August 1995



APPROVED FOR PUBLIC RELEASE; DISTRIBUTION IS UNLIMITED.

19950927 059

DTIC QUALITY INSPECTED 6

NOTICES

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

The citation of trade names and names of manufacturers in this report is not to be construed as official Government endorsement or approval of commercial products or services referenced herein.

REPORT DOCUMENTATION PAGE			Form Approved OMB NO. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comment regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE August 1995		3. REPORT TYPE AND DATES COVERED Technical Report
4. TITLE AND SUBTITLE POISSON'S RATIO FOR POLED ELECTROCERAMICS			5. FUNDING NUMBERS	
6. AUTHOR(S) Arthur Ballato				
7. PERFORMING ORGANIZATION NAMES(S) AND ADDRESS(ES) US Army Research Laboratory (ARL) Physical Sciences Directorate ATTN: AMSRL-PS Fort Monmouth, NJ 07703-5601			8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-432	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES)			10. SPONSORING / MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.			12 b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) General expressions for Poisson's ratio are derived for arbitrary orientations in hexagonal point groups; simplified forms are given for cases involving symmetry directions. Applications are made to piezoelectric ceramics.				
14. SUBJECT TERMS Hexagonal stiffness; transformation matrix; bulk modulus			15. NUMBER IF PAGES 18	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OR REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT UL	

Table of Contents

<u>Section</u>	<u>Page</u>
Abstract	1
Introduction	1
Expressions Relating Hexagonal Stiffnesses and Compliances	2
Definition of Poisson's Ratio for Crystals	5
Relations for Rotated Hexagonal Compliances - General	5
Transformation Matrix for General Rotations	6
Poisson's Ratios for Specific Orientations	6
Bulk Modulus	9
Application to Piezoceramics	9
Conclusions	11
Bibliography	12
<hr/>	
Figure 1. Limits on the Lamé constants of isotropic solids. Symbols employed are: C, cement; G, gas; GL, glass; IL, incompressible liquid; L, liquid; M, metal, ceramic; P, plastic; R, rubber; V, vacuum.	3
Table 1. RELATIONS AMONG ISOTROPIC ELASTIC PARAMETERS	4
Table 2. POISSON'S RATIO, YOUNG'S MODULUS, AND COMPRESSIBILITY OF SELECTED PIEZOCERAMICS	10

POISSON'S RATIO FOR POLED ELECTROCERAMICS

Abstract

General expressions for Poisson's ratio are derived for arbitrary orientations in hexagonal point groups; simplified forms are given for cases involving symmetry directions. Applications are made to piezoelectric ceramics.

Introduction

Poisson's ratio, ν , is defined for isotropic media as the quotient of lateral contraction to longitudinal extension arising from application of a simple tensile stress. The ratio finds application in a number of areas of applied elasticity and solid mechanics, for example, as indication of the mechanical coupling between various vibrational modes of motion. Future high-tech applications will involve mechanically resonant microstructures integrated with electronic and optical circuitry. These will require extension of Poisson's ratio considerations to a variety of crystalline and polycrystalline substances.

In most materials, the dimensionless number ν is positive. In crystals and poled electroceramics, ν takes on different values, depending on the directions of stress and strain chosen. The maximum value of $\nu = +1/2$ is obtained in the incompressible medium limit, where volume is preserved; for ordinary materials, values of $+1/4$ to $+1/3$ are typical, but in crystals ν may vanish, or take on negative values. In order to provide a synoptic yet relatively uncomplicated picture, Figure 1 sketches the bounds on ν as function of the traditional Lamé constants of an isotropic medium. Table 1 relates various elastic measures for substances or conditions indicated in the figure, or discussed in the sequel. Analytical formulas for Poisson's ratio are expressed in terms of elastic moduli. For the case of crystals of general anisotropy, these expressions are quite unwieldy, but for substances in the hexagonal system the symmetry elements reduce the complexity considerably. Many of the materials under consideration for future microdevices are characterized by hexagonal symmetry.

Accession For	
NTIS	CRA&I <input checked="checked" type="checkbox"/>
DTIC	TAB <input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	

The hexagonal crystal system¹⁻³ comprises seven point groups (6-bar m2, 622, 6mm, 6/m mm, 6-bar, 6, and 6/m), and includes a number of the binary semiconductor systems, and their alloys. These have the piezoelectric wurtzite structure; examples are GaN and AlN. The family of poled electroceramics, including BaTiO₃, PZT, and related alloys are characterized by symmetry ∞ mm, that is, they are transversely isotropic. However, this symmetry is equivalent to 6mm for all tensor properties up to and including rank five;⁴ this includes elasticity. All hexagonal groups have the same elastic matrix scheme, so for our purposes it is not necessary to distinguish between them.

Expressions Relating Hexagonal Stiffnesses and Compliances

Relations for Poisson's ratio are most simply expressed in terms of the elastic compliances [$s_{\lambda\mu}$]. It is often the case, however, that the most accurate determinations of the elastic constants (resonator and transit-time methods) yield values for the stiffnesses [$c_{\lambda\mu}$] directly;⁵ the conversion relations are given below. For the hexagonal system, the elastic stiffness and compliance matrices have identical form. Referred to the x_k axes as defined in the IEEE Standard,⁵ the matrices are:

c_{11}	c_{12}	c_{13}	0	0	0	s_{11}	s_{12}	s_{13}	0	0	0
c_{12}	c_{11}	c_{13}	0	0	0	s_{12}	s_{11}	s_{13}	0	0	0
c_{13}	c_{13}	c_{33}	0	0	0	s_{13}	s_{13}	s_{33}	0	0	0
0	0	0	c_{44}	0	0	0	0	0	s_{44}	0	0
0	0	0	0	c_{44}	0	0	0	0	0	s_{44}	0
0	0	0	0	0	c_{66}	0	0	0	0	0	s_{66}

Stiffness and compliance are matrix reciprocals; the five independent components of each are related by:

$$\begin{aligned}
 (c_{11} + c_{12}) &= s_{33} / S ; & (c_{11} - c_{12}) &= 1 / (s_{11} - s_{12}) \\
 c_{13} &= -s_{13} / S ; & c_{33} &= (s_{11} + s_{12}) / S \\
 c_{44} &= 1 / s_{44} ; & S &= s_{33} (s_{11} + s_{12}) - 2 s_{13}^2
 \end{aligned}$$

In addition, one has the relation $s_{66} = 2(s_{11} - s_{12})$. The compliances are given in terms of the stiffnesses simply by interchange of symbols, but with $c_{66} = (c_{11} - c_{12})/2$. The equality of the 11 and 22 components together with the given relations between the 66, 11 and 12 components imply transverse isotropy; that is, all directions perpendicular to the unique six-fold axis (i.e., in the basal plane) are elastically equivalent.




Figure 1. Limits on the Lamé constants of isotropic solids.
 (Symbols: C, cement; G, gas; GL, glass; IL, incompressible liquid; L, liquid; M, metal, ceramic; P, plastic; R, rubber; V, vacuum)

TABLE 1. RELATIONS AMONG ISOTROPIC ELASTIC PARAMETERS.

SUBSTANCE OR CONDITION	ν	λ	μ	Y	κ	v_{sh}/v_{long}
Ideal fluids	1/2	λ	0	0	λ	0
Many metals	1/3	2μ	μ	$8\mu/3$	$8\mu/3$	1/2
Poisson relation	1/4	μ	μ	$5\mu/2$	$5\mu/3$	$1/\sqrt{3}$
Pure rigidity	0	0	μ	2μ	$2\mu/3$	$1/\sqrt{2}$
Perfect compressibility	- 1	$-2\mu/3$	μ	0	0	$\sqrt{3}/2$
Incompressible liquids	1/2	∞	0	0	∞	0
Incompressible solids	---	∞	∞	∞	∞	---

[v_{sh}/v_{long}] is ratio of shear to longitudinal wave velocities

Definition of Poisson's Ratio for Crystals

Poisson's ratio for crystals¹ is defined in general as $\nu_{ji} = -s_{ij}' / s_{ii}'$, where x_j is the direction of the longitudinal extension, x_i is the direction of the accompanying lateral contraction, and the s_{ij}' and s_{jj}' are the appropriate elastic compliances referred to this right-handed axial set. It suffices to take x_1 as the direction of the longitudinal extension; then two Poisson's ratios are defined by the orientations of the lateral axes x_2 and x_3 : $\nu_{21} = -s_{12}' / s_{11}'$ and $\nu_{31} = -s_{13}' / s_{11}'$. Application of the definition requires specification of the orientation of the x_k coordinate set with respect to the crystallographic directions, and transformation of the compliances accordingly. The influence of piezoelectricity on the Poisson's ratio is neglected here, but may be incorporated in a straightforward manner. For completeness, we note that in crystals the Young's modulus Y is a function of orientation, and is defined by $s_{11}' = 1/Y$. The Lamé moduli λ , μ for isotropic elastic bodies are defined as $\lambda = c_{12} = c_{13} = c_{23}$, and $\mu = c_{44} = c_{55} = c_{66}$. The remaining nonzero isotropic stiffnesses are $(\lambda + 2\mu) = c_{11} = c_{22} = c_{33}$.

Relations for Rotated Hexagonal Compliances - General

The unprimed compliances are referred to a set of right-handed orthogonal axes related to the crystallographic axes in the manner defined by the IEEE standard.⁵ Direction cosines a_{mn} relate the transformation from these axes to the set specifying the directions of the applied longitudinal extension (x_1), and the resulting lateral contractions (x_2 and x_3). General expressions for the transformed hexagonal compliances that enter the formulas for ν_{21} and ν_{31} are:

$$s_{11}' = s_{11} [a_{11}^2 + a_{12}^2]^2 + s_{33} [a_{13}^4] + (s_{44} + 2s_{13}) [a_{13}^2] [a_{11}^2 + a_{12}^2]$$

$$s_{12}' = s_{11} [a_{11} a_{21} + a_{12} a_{22}]^2 + s_{33} [a_{13}^2 a_{23}^2] + \\ s_{44} [a_{13} a_{23}] [a_{11} a_{21} + a_{12} a_{22}] + s_{12} [a_{11} a_{22} - a_{12} a_{21}]^2 + \\ s_{13} [a_{23}^2 [a_{11}^2 + a_{12}^2] + a_{13}^2 [a_{21}^2 + a_{22}^2]]$$

$$s_{13}' = s_{11} [a_{11} a_{31} + a_{12} a_{32}]^2 + s_{33} [a_{13}^2 a_{33}^2] + \\ s_{44} [a_{13} a_{33}] [a_{11} a_{31} + a_{12} a_{32}] + s_{12} [a_{11} a_{32} - a_{12} a_{31}]^2 + \\ s_{13} [a_{33}^2 [a_{11}^2 + a_{12}^2] + a_{13}^2 [a_{31}^2 + a_{32}^2]]$$

Transformation Matrix for General Rotations

Poisson's ratio for the most general case may be derived by considering the transformation matrix for a combination of three coordinate rotations: a first rotation about x_3 by angle φ , a second rotation about the new x_1 by angle θ , and a third rotation about the resulting x_2 by angle ψ . When these angles are set to zero, the x_1, x_2, x_3 axes coincide respectively with the reference crystallographic directions. For nonzero angles, the direction cosines a_{mn} are as follows, with the abbreviations $c(\theta)$ and $s(\theta)$ for $\cos(\theta)$ and $\sin(\theta)$, etc.:

$$\begin{array}{lll} [c(\varphi)c(\psi) - s(\varphi)s(\theta)s(\psi)] & [s(\varphi)c(\psi) + c(\varphi)s(\theta)s(\psi)] & [-c(\theta)s(\psi)] \\ [-s(\varphi)c(\theta)] & [c(\varphi)c(\theta)] & [s(\theta)] \\ [c(\varphi)s(\psi) + s(\varphi)s(\theta)c(\psi)] & [s(\varphi)s(\psi) - c(\varphi)s(\theta)c(\psi)] & [c(\theta)c(\psi)] \end{array}$$

Substitution of these a_{mn} into the expressions for s_{11}' , s_{12}' , and s_{13}' , and thence into the formulas $\nu_{21} = -s_{12}' / s_{11}'$ and $\nu_{31} = -s_{13}' / s_{11}'$ formally solves the problem for specified values of φ , θ , and ψ . The condition of transverse isotropy stated above, however, renders all results independent of azimuthal angle φ , which is henceforth ignored.

Poisson's Ratios for Specific Orientations

1) Longitudinal extension in the basal plane: $\psi = 0$; θ arbitrary.
Direction cosines are: $a_{11} = 1$; $a_{22} = a_{33} = c(\theta)$; $a_{12} = -a_{21} = s(\theta)$

Rotated compliances are:

$$s_{11}' = s_{11}$$

$$s_{12}' = s_{12} \cos^2(\theta) + s_{13} \sin^2(\theta) = s_{12} + (s_{13} - s_{12}) \sin^2(\theta)$$

$$s_{13}' = s_{12} \sin^2(\theta) + s_{13} \cos^2(\theta) = s_{13} - (s_{13} - s_{12}) \sin^2(\theta)$$

Poisson's ratios are:

$$\nu_{21} = -[s_{12} + (s_{13} - s_{12}) \sin^2(\theta)] / s_{11}$$

$$\nu_{31} = -[s_{13} - (s_{13} - s_{12}) \sin^2(\theta)] / s_{11}$$

When $\theta = 0$,

$$\nu_{21} = -s_{12} / s_{11}$$

$$\nu_{31} = -s_{13} / s_{11}$$

When $\theta = \pi/4$,

$$\nu_{21} = \nu_{31} = -(s_{12} + s_{13}) / 2 s_{11}$$

2) Longitudinal extension at an angle ψ from the basal plane; the x_2 axis in the basal plane: $\theta = 0$; ψ arbitrary.

Direction cosines are: $a_{22} = 1$; $a_{11} = a_{33} = c(\psi)$; $-a_{13} = a_{31} = s(\psi)$

Rotated compliances are:

$$s_{11}' = s_{11} [c^4(\psi)] + s_{33} [s^4(\psi)] + (s_{44} + 2 s_{13}) [c^2(\psi) s^2(\psi)]$$

$$s_{12}' = s_{12} [c^2(\psi)] + s_{13} [s^2(\psi)] = s_{12} + (s_{13} - s_{12}) [s^2(\psi)]$$

$$s_{13}' = s_{13} + s_2 [c^2(\psi) s^2(\psi)]; \quad s_2 = (s_{11} + s_{33} - (s_{44} + 2 s_{13}))$$

Poisson's ratios are:

$$\nu_{21} = -s_{12}' / s_{11}'$$

$$\nu_{31} = -s_{13}' / s_{11}'$$

When $\psi = \pi/4$,

$$\nu_{21} = -2 (s_{12} + s_{13}) / (s_0 + s_{44})$$

$$\nu_{31} = -(s_0 - s_{44}) / (s_0 + s_{44}); \quad s_0 = (s_{11} + s_{33} + 2 s_{13})$$

When $\psi = \pi/2$,

$$\nu_{21} = \nu_{31} = -s_{13} / s_{33}$$

Poisson's ratio is isotropic when the longitudinal extension is along the six-fold symmetry axis.

3) Longitudinal extension out of the basal plane: θ and ψ arbitrary.
Direction cosines are:

$$\begin{array}{lll} [c(\psi)] & [s(\theta)s(\psi)] & [-c(\theta)s(\psi)] \\ [0] & [c(\theta)] & [s(\theta)] \\ [s(\psi)] & [-s(\theta)c(\psi)] & [c(\theta)c(\psi)] \end{array}$$

Rotated compliances are:

$$\begin{aligned} s_{11}' &= s_{11} [s^2(\theta)s^2(\psi) + c^2(\psi)]^2 + s_{33} [c^4(\theta)s^4(\psi)] + \\ &\quad (s_{44} + 2s_{13}) [c^2(\theta)s^2(\psi)][s^2(\theta)s^2(\psi) + c^2(\psi)] \\ s_{12}' &= s_{12} [c^2(\theta)c^2(\psi)] + s_{13} [s^2(\theta)c^2(\psi) + s^2(\psi)] + \\ &\quad s_2 [c^2(\theta)s^2(\theta)s^2(\psi)] \\ s_{13}' &= s_{12} [s^2(\theta)] + s_{13} [c^2(\theta)] + s_2 [c^4(\theta)c^2(\psi)s^2(\psi)] \end{aligned}$$

Poisson's ratios are:

$$\begin{aligned} \nu_{21} &= -s_{12}' / s_{11}' \\ \nu_{31} &= -s_{13}' / s_{11}' \end{aligned}$$

These results reduce to those of Case 1) when $\psi = 0$, and to those of Case 2) when $\theta = 0$.

4) Longitudinal extension at an angle ψ from the basal plane: first rotation about x_2 by angle ψ , followed by a second rotation about x_1 by angle χ .
Direction cosines are:

$$\begin{array}{lll} [c(\psi)] & [0] & [-s(\psi)] \\ [s(\psi)s(\chi)] & [c(\chi)] & [c(\psi)s(\chi)] \\ [s(\psi)c(\chi)] & [-s(\chi)] & [c(\psi)c(\chi)] \end{array}$$

Rotated compliances are:

$$s_{11}' = s_{11} [c^4(\psi)] + s_{33} [s^4(\psi)] + (s_{44} + 2 s_{13}) [c^2(\psi)s^2(\psi)]$$

$$s_{12}' = s_{12} [c^2(\psi)c^2(\chi)] + s_{13} [s^2(\psi)c^2(\chi) + s^2(\chi)] + s_2 [c^2(\psi)s^2(\psi)s^2(\chi)]$$

$$s_{13}' = s_{12} [c^2(\psi)s^2(\chi)] + s_{13} [s^2(\psi)s^2(\chi) + c^2(\chi)] + s_2 [c^2(\psi)s^2(\psi)c^2(\chi)]$$

Poisson's ratios are:

$$\nu_{21} = - s_{12}' / s_{11}'$$

$$\nu_{31} = - s_{13}' / s_{11}'$$

These results reduce to those of Case 1) when $\psi = 0$, and to those of Case 2) when $\chi = 0$.

Bulk Modulus

The bulk modulus, or compressibility, κ , is often associated with considerations requiring use of the Poisson's ratio. It is defined as the hydrostatic pressure required to bring about a unit relative change of volume of a substance; it is always positive. For solids of the most general anisotropy, κ is found from the relation

$$[(s_{11} + s_{22} + s_{33}) + 2 (s_{23} + s_{13} + s_{12})] = 1 / \kappa.$$

For the hexagonal system this reduces to:

$$[(2 s_{11} + s_{33}) + 2 (2 s_{13} + s_{12})] = 1 / \kappa.$$

Application to Piezoceramics

The poling state of piezoceramics nearly always encountered in present commercial practice is either parallel, or lateral, to the major surfaces of the device. This is because the effective piezoelectric coupling is thereby maximized by the electrode placements. Newer configurations, currently under development for microelectromechanical structures (MEMS) applications, utilize more general orientations that take advantage of the achievable differences in Poisson's ratios in different directions. Table 2 gives some representative examples, based on the relations derived above; entries are computed from data in Refs. 6 and 7.

TABLE 2. POISSON'S RATIO, YOUNG'S MODULUS, AND COMPRESSIBILITY OF SELECTED PIEZOCERAMICS.

COMPOSITION	θ°, ψ°	ν_{21}	ν_{31}	Y	κ
Ba Ti O ₃	0,0	0.305	0.333	117.0	106.3
PZT-4	45,0	0.380	0.380	81.3	92.9
PZT-5A	0,45	0.380	0.392	58.6	89.1
PZT 52/48	45,45	0.401	0.354	63.7	93.5
PZT 65/35	0,0	0.290	0.395	110.3	95.6
Pb _{0.76} Ca _{0.24} Ti O ₃	45,0	0.399	0.399	136.1	69.6
Pb _{0.96} La _{0.04} Ti O ₃	0,45	0.232	0.163	147.2	81.4
Pb _{0.89} Nd _{0.11} Ti O ₃	45,45	0.235	0.262	149.4	94.0

[Y and κ in GPa]

Conclusions

Poisson's ratio, with respect to rotated coordinate axes, for hexagonal materials, and particularly, poled ferroelectric ceramics, has been obtained. All results are independent of rotations about the six-fold axis. A number of simple cases are of particular interest:

- For longitudinal extension in the basal plane, $\psi = 0$:

$$\text{When } \theta = 0: v_{21} = -s_{12} / s_{11}; v_{31} = -s_{13} / s_{11}$$

$$\text{When } \theta = \pi/4: v_{21} = v_{31} = -(s_{12} + s_{13}) / 2 s_{11}$$

- For longitudinal extension at an angle ψ from the basal plane:

$$\text{When } \theta = 0; \psi = \pi/4: v_{21} = -2 (s_{12} + s_{13}) / (s_0 + s_{44})$$

$$v_{31} = - (s_0 - s_{44}) / (s_0 + s_{44}); s_0 = (s_{11} + s_{33} + 2 s_{13})$$

$$\text{When } \theta = \pi/4; \psi = \pi/4: s_2 = (s_{11} + s_{33} - (s_{44} + 2 s_{13}))$$

$$v_{21} = - [4 s_{12} + 12 s_{13} + 2 s_2] / [12 s_{11} + 4 s_{33} - 3 s_2]$$

$$v_{31} = - [8 s_{12} + 8 s_{13} + s_2] / [12 s_{11} + 4 s_{33} - 3 s_2]$$

$$\text{When } \psi = \pi/4; \chi = \pi/4: s_2 = (s_{11} + s_{33} - (s_{44} + 2 s_{13}))$$

$$v_{21} = v_{31} = - [s_{12} + 3 s_{13} + s_2 / 2] / [2 (s_{11} + s_{33}) - s_2]$$

- For longitudinal extension along the six-fold axis:

$$v_{21} = v_{31} = -s_{13} / s_{33}$$

Bibliography

- [1] W G Cady, Piezoelectricity, McGraw-Hill, New York, 1946; Dover, New York, 1964.
- [2] "IRE Standards on Piezoelectric Crystals, 1949," Proc. IRE, Vol. 37, No. 12, December 1949, pp. 1378-1395.
- [3] J F Nye, Physical Properties of Crystals, Clarendon Press, Oxford, 1957; Oxford University Press, 1985.
- [4] H J Juretschke, Crystal Physics, W A Benjamin, Reading, MA, 1974.
- [5] "IEEE Standard on Piezoelectricity," ANSI/IEEE Standard 176-1987, The Institute of Electrical and Electronics Engineers, New York, 10017.
- [6] B Jaffe, W R Cook, Jr, and H Jaffe, Piezoelectric Ceramics, Academic Press, New York, 1971.
- [7] Landolt-Börnstein, Numerical Data and Functional Relationships in Science and Technology, New Series, Group III: Crystal and Solid State Physics, Volumes III/1, 1966; III/11, 1979; and III/29a, 1992. Springer-Verlag, Berlin, New York.

ARMY RESEARCH LABORATORY
PHYSICAL SCIENCES DIRECTORATE
MANDATORY DISTRIBUTION LIST

February 1995
Page 1 of 2

Defense Technical Information Center*
ATTN: DTIC-OCC
Cameron Station (Bldg 5)
Alexandria, VA 22304-6145
(*Note: Two DTIC copies will be sent
from STINFO office, Ft Monmouth, NJ)

Advisory Group on Electron Devices
ATTN: Documents
Crystal Square 4
1745 Jefferson Davis Highway, Suite 500
(2) Arlington, VA 22202

Director
US Army Material Systems Analysis Actv
ATTN: DRXSYPMP
(1) Aberdeen Proving Ground, MD 21005

Commander, CECOM
R&D Technical Library
Fort Monmouth, NJ 07703-5703
(1) AMSEL-IM-BM-I-L-R (Tech Library)
(3) AMSEL-IM-BM-I-L-R (STINFO Ofc)

Commander, AMC
ATTN: AMCDE-SC
5001 Eisenhower Ave.
(1) Alexandria, VA 22333-0001

Director
Army Research Laboratory
ATTN: AMSRL-D (John W. Lyons)
2800 Powder Mill Road
(1) Adelphi, MD 20783-1197

Director
Army Research Laboratory
ATTN: AMSRL-DD (COL Thomas A. Dunn)
2800 Powder Mill Road
(1) Adelphi, MD 20783-1197

Director
Army Research Laboratory
2800 Powder Mill Road
Adelphi, MD 20783-1197
(1) AMSRL-OP-SD-TA (ARL Records Mgt)
(1) AMSRL-OP-SD-TL (ARL Tech Library)
(1) AMSRL-OP-SD-TP (ARL Tech Publ Br)

Directorate Executive
Army Research Laboratory
Physical Sciences Directorate
Fort Monmouth, NJ 07703-5601
(1) AMSRL-PS
(1) AMSRL-PS-T (M. Hayes)
(1) AMSRL-OP-FM-RM
(22) Originating Office

ARMY RESEARCH LABORATORY
PHYSICAL SCIENCES DIRECTORATE
SUPPLEMENTAL DISTRIBUTION LIST
(ELECTIVE)

February 1995
Page 2 of 2

- | | |
|---|--|
| <p>Deputy for Science & Technology
Office, Asst Sec Army (R&D)
(1) Washington, DC 20310</p> <p>HQDA (DAMA-ARZ-D/
Dr. F.D. Verderame)
(1) Washington, DC 20310</p> <p>Director
Naval Research Laboratory
ATTN: Code 2627
(1) Washington, DC 20375-5000</p> <p>USAF Rome Laboratory
Technical Library, FL2810
ATTN: Documents Library
Corridor W, STE 262, RL/SUL
26 Electronics Parkway, Bldg 106
Griffiss Air Force Base
(1) NY 13441-4514</p> <p>Dir, ARL Battlefield
Environment Directorate
ATTN: AMSRL-BE
White Sands Missile Range
(1) NM 88002-5501</p> <p>Dir, ARL Sensors, Signatures,
Signal & Information Processing
Directorate (S3I)
ATTN: AMSRL-SS
2800 Powder Mill Road
(1) Adelphi, MD 20783-1197</p> <p>Dir, CECOM Night Vision/
Electronic Sensors Directorate
ATTN: AMSEL-RD-NV-D
(1) Fort Belvoir, VA 22060-5677</p> <p>Dir, CECOM Intelligence and
Electronic Warfare Directorate
ATTN: AMSEL-RD-IEW-D
Vint Hill Farms Station
(1) Warrenton, VA 22186-5100</p> | <p>Cdr, Marine Corps Liaison Office
ATTN: AMSEL-LN-MC
(1) Fort Monmouth, NJ 07703-5033</p> |
|---|--|